LI315

White Voided In-Mold Label Film, Ultra High Yield



Last update: 01-Oct-2014

DESCRIPTION:


Gulf Pack LI315 is a white voided film, one side glossy and other side matte, both sides treated, with ultra high yield property ($\rho = 0.58$).

PRODUCT FEATURES:

Ultra high yield due to very low density Excellent machinability.
High gloss in one side and matte on other side
Good printability
High opacity and high stiffness

APPLICATIONS:

In-Mold label
Rotogravure & flexographic printing



PROPERTIES			UNIT	TYPICAL VALUES		TEST METHOD.
PHYSICAL	Thickness		Microns	60	70	ACTM D 274
			Gauge	240	280	ASTM D 374
	Grammage		g/m²	34.8	40.6	*GPIM
			lbs/ream	21.39	24.95	
	Yield		m²/kg	28.70	24.60	
			in²/lb	20,220	17,331	
	Density		g/cc	0.58		
	Coefficient of Friction (Film/Film)			0.35		ASTM D 1894
	Surface Tension (Treated Side)		dynes/cm	38		ASTM D 2578
OPTICAL	Opacity		%	85		ASTM D 589-97
OFTICAL	Gloss (45°)			70		ASTM D 2457
MECHANICAL	Tensile Strength at Break	*MD	kg/mm² -	8		ASTM D 882
		*TD	kg/IIIII-	16		
		MD	psi -	11,376		
		TD		22,752		
	Elongation at Break	MD	%	135		ASTM D 882
		TD		40	40	
THERMAL	Thermal Shrinkage	MD	%	< 4.0		GPIM (122 % 2 (222 % 2)
		TD		< 2.	0	(120°C (248°F), 5 min, air)

^{*} GPIM - Gulf Pack Internal Method

Gulf Pack LI315 films comply with EU Regulation 10/2011/EC and USA FDA Code of Federal Regulations CFR21 section 177.1520 (c) 1.1 and are suitable for use in packaging, carrying and transporting foodstuffs.

The information contained in this technical leaflet illustrates typical values only and are to the best of our knowledge. Since the conditions under which our films may be used are beyond our control, such values are declared without warranty or guarantee.

Bi-axially oriented polypropylene films age with time and will exhibit deterioration of some properties if not stored in a suitable environment at a temperature 30°C or below. We strongly advise our customers to use recommended storage conditions and consume products before 6 months from date of production in our plant.

Gulf Pack LI315 surface treatment indication is on both sides (B).

Detailed advice regarding other specific applications of **Gulf Pack LI315** and other films in the Gulf Pack range is available upon request.

^{*}MD – Machine Direction

^{*}TD - Transverse Direction